

Alpha Resources, Inc. Certificate Of Analysis

AR-2776
ULTIMATE COAL STANDARD
LOT #776105 LID #703105
DRIED BASIS VALUES

| | | | |
|-----------------------------|-------|-----------------------------------|--------|
| Proximate Analysis | | Ultimate Analysis | |
| % Ash..... | 9.00 | % Carbon..... | 79.20 |
| % Volatile Matter..... | 25.20 | % Hydrogen..... | 4.77 |
| % Fixed Carbon..... | 65.85 | % Nitrogen..... | 1.40 |
| % Sulfur..... | 0.85 | Btu..... | 14,085 |
| Mineral Analysis | | Sulfur Forms | |
| Silica..... | 49.91 | % Pyritic..... | 0.12 |
| Alumina..... | 29.68 | % Organic..... | 0.69 |
| Titania..... | 1.03 | % Sulfate..... | 0.04 |
| Ferric Oxide..... | 5.54 | Ash Fusion Temperature | |
| Calcium Oxide..... | 4.79 | Initial Deformation Red..... | 2589 |
| Magnesium Oxide..... | 0.88 | Initial Deformation Oxd..... | 2694 |
| Potassium Oxide..... | 2.17 | Softening-Red H=W..... | 2670 |
| Sodium Oxide..... | 0.29 | Softening-Oxd H=W..... | 2700 |
| Sulfur Trioxide..... | 1.23 | Softening-Red H=1/2w..... | 2687 |
| Phosphorus Pentoxide..... | 2.55 | Softening-Oxd H=1/2w..... | 2700 |
| Strontium Oxide..... | 0.34 | Fluid-Reducing..... | 2700 |
| Barium Oxide..... | 0.28 | Fluid-Oxidizing..... | 2700 |
| Manganese Oxide..... | 0.03 | Temperature In Degrees F..... | |
| Undetermined..... | 1.28 | | |

The Following ASTM Procedures Were Employed In The Analysis Of All Samples:

| | | | |
|------------------------|-------------|-------------------|-------------|
| Preparation..... | ASTM D 2013 | Ash Analysis..... | ASTM D 3682 |
| Carbon & Hydrogen..... | ASTM D 3178 | Chlorine..... | ASTM D 2361 |
| Volatile Matter..... | ASTM D 3175 | Fusibilities..... | ASTM D 1857 |
| Sulfur..... | ASTM D 3177 | BTU..... | ASTM D 2015 |
| Nitrogen..... | ASTM D 3179 | Sulfur Forms..... | ASTM D 2492 |
| Ash..... | ASTM D 3174 | | |

The material used in production of this standard was sampled in accordance with ARI 031. The above values relate only to the material used to produce this standard.

The overall direction and coordination of the analytical measurements leading to certification were performed by J.R. Shingledecker at Alpha Resources.

Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Alpha Resources be liable for incidental or consequential damages.

This is a Certified Reference Material (CRM). For good laboratory practice it is recommended that all standards be verified prior to use.

EXPIRATION DATE
THIS CRM IS VALID FOR TWO YEARS FROM THE DATE OF PURCHASE WHICH
APPEARS ON THE BOTTLE

J.R. Shingledecker

P.O. Box 199 3090 Johnson Road Stevensville, MD 21153 USA Phone (269) 465-5559 Fax (269) 465-3629

www.alpharesources.com